Technical NI		TTA BELT POLY	
	Data Sheet extended by P-044	HA-2000G	NITTA
Applications			
	Item	Description	Remarks
Specification	Construction	1) 2) 3) 2/2/2/2/2/2/2/2/2/2/2/2/2/2/2/2/2/2/2/	①NBR (Ground surface, Blue) ②PA Fabric ③PA Film ④NBR (Ground surface, Blue)
Dimensions	Antistatic	Yes	
	Width	20 to 325 [mm]	
	Length	800 to 105,000 [mm]	
men	Thickness	3.7 [mm]	
٥	Joint	Skived joint Adhesive Polybond A and E	
Properties	Tensile strength	600 [N/mm]	Test speed: 50mm/min
	Elongation at break	20 [%]	Ambient condition: 23°C,50%R.H.
	Standard elongation	2 [%]	
	Tension at 2 [%]	30 [N/mm]	Ambient condition: 23°C,50%R.H.
	Minimum pulley dia.	200 [mm]	
	Operating temp.	-20 to +80°C	
	Coefficient of	0.5 to 0.6(Steel) (Both side)	Measurement condition: 7kPa, 1mm/s
	friction		Ambient condition: 23°C,50%R.H.
	Mass	4.2 [kg/m2]	
Features			
			Industrial Products Div.