Technical NI		TTA BELT POLY	
	Data Sheet  P-155	LA-350	NITTA
Applications			
	Item	Description	Remarks
Specification	Construction	(1) (2) (3) (4)	①NBR (Textured Pattern, Blue) ②PA Fabric ③PA Film ④NBR (Textured Pattern, Blue)
Dimensions	Antistatic	Yes	
	Width	6 to 325 [mm]	
	Length	300 to 105,000 [mm]	
	Thickness	1.45 [mm]	
	Joint	Skived joint Adhesive Polybond A and E	
	Tensile strength	105 [N/mm]	Test speed: 50mm/min
	Elongation at break	20 [%]	Ambient condition: 23°C,50%R.H.
Properties	Standard elongation	2 [%]	
	Tension at 2 [%]	5.2 [N/mm]	Ambient condition: 23°C,50%R.H.
	Minimum pulley dia.	35 [mm]	
	Operating temp.	-20 to +80°C	
	Coefficient of	0.5 to 0.6(Steel) (Both side)	Measurement condition: 7kPa, 1mm/s
	friction		Ambient condition: 23°C,50%R.H.
	Mass	1.6 [kg/m2]	
Features			
			Industrial Products Div.